

BESTUNG CARBIDE INC.

TANTALUM CARBIDE & SOLID SOLUTION POWDER

Grade Available for Tantalum Carbide Powder TaC-1, TaC-2

Grade	Chemical Composition (%)											Fsss (micron)
	C Total	C free	Nb	Fe	Si	O	N	Ti	Na	Al	Ca	
TaC-1	>6.20	<0.15	<0.15	<0.08	<0.01	<0.35	<0.02	<0.01	<0.015	<0.01	<0.01	<1.0
TaC-2	>6.20	<0.10	<0.15	<0.06	<0.015	<0.20	<0.025	<0.01	<0.015	<0.01	<0.015	1.01-2.0

Grade Available for Tantalum & Niobium Solid Solution Powder TaNb-1, TaNb-2, TaNb-3

Grade	Chemical Composition (%)												Fsss (micron)
	Ta	Nb	C Total	C Free	Fe	Si	O	N	Ti	Na	Al	Ca	
TaNb-1	69.5-72.5	19.6-21.6	6.7-7.7	<0.15	<0.15	<0.02	<0.2	<0.2	<0.5	<0.015	<0.015	<0.01	2.0-5.0
TaNb-2	64.1-67.1	25.4-27.8	7.3-8.3	<0.15	<0.15	<0.02	<0.2	<0.2	<0.5	<0.015	<0.015	<0.01	2.0-5.0
TaNb-3	54.7-57.3	33.7-36.3	7.6-8.6	<0.15	<0.15	<0.02	<0.2	<0.2	<0.5	<0.015	<0.015	<0.01	2.0-5.0

Packing: Materials in plastic bag within steel drum, net each 50 kgs

Quality: Assay results are available for each lot

7883 Jackson Road, Ann Arbor, MI 48103, USA
Tel: 734-424-9327, Fax: 734-424-9328
Email: sales@bestungcarbideinc.com