

# BESTUNG CARBIDE INC.

---

## TUNGSTEN POWDER (W)

### Grade Available

| Grade | Fsss(um)  | Oxygen<br>(% max) | Fe<br>(% max) | Trace Element<br>( ppm,max.) |     |
|-------|-----------|-------------------|---------------|------------------------------|-----|
| BW06  | 0.5-0.7   | 0.4               | 0.01          | Al                           | 20  |
| BW07  | 0.6-0.8   | 0.35              | 0.01          | Ca                           | 20  |
| BW08  | 0.7-0.9   | 0.3               | 0.01          | Cr                           | 300 |
| BWC09 | 0.9-1.1   | 0.2               | 0.01          | Cu                           | 20  |
| BW12  | 1.0-1.35  | 0.15              | 0.02          | K                            | 15  |
| BW15  | 1.35-1.75 | 0.15              | 0.02          | Mg                           | 20  |
| BW20  | 1.75-2.35 | 0.10              | 0.02          | Mn                           | 20  |
| BW25  | 2.35-2.85 | 0.10              | 0.02          | Mo                           | 100 |
| BW30  | 2.75-3.25 | 0.10              | 0.02          | Na                           | 20  |
| BW35  | 3.25-3.75 | 0.10              | 0.02          | Ni                           | 100 |
| BW40  | 3.75-4.35 | 0.10              | 0.02          | Pb                           | 5   |
| BW45  | 4.35-4.85 | 0.10              | 0.02          | Si                           | 40  |
| BW60  | 5.50-6.50 | 0.08              | 0.02          | Sn                           | 5   |
| BW80  | 7.0-9.0   | 0.08              | 0.02          | S                            | 10  |
| BW100 | 10.0-15.0 | 0.08              | 0.02          | Sb                           | 10  |
| BW200 | 15.0-25.0 | 0.08              | 0.03          | Ti                           | 10  |
| BW300 | 25.0-35.0 | 0.08              | 0.03          | V                            | 10  |
| BW400 | 35.0-40.0 | 0.08              | 0.03          |                              |     |

1) Fsss size range may vary by customer requirements.

2) Typical trace elements are much lower than Specification.

**Packing: Materials in plastic bag within steel drum, net each 50kgs or 200kgs**

**Quality: Assay results are available for each lot**

---

**7883 Jackson Road, Ann Arbor, MI 48103, USA**  
**Tel: 734-424-9327, Fax: 734-424-9328**  
**Email: sales@bestungcarbideinc.com**