

BESTUNG CARBIDE INC.

YELLOW TUNGSTEN OXIDE (YTO)

Grade Available
YTO-I

Appearance: Light Yellow Powder


Chemical Composition:

Main component content:


WO₃ 99.97 % min (by difference)

Trace Element (% max.)

Al	0.0005
As	0.001
Bi	0.0001
Ca	0.001
Co	0.001
Cr	0.001
Cu	0.0003
Fe	0.001
K	0.001
Mg	0.0007
Mn	0.001
Mo	0.002
Na	0.001
Ni	0.0007
P	0.0007
Pb	0.0001
S	0.0007
Sb	0.0008
Si	0.001
Sn	0.0002
Ti	0.001
V	0.001



X50



X300

Packing: Materials in plastic bag within steel drum, net each 200 kgs

Quality: Assay results are available for each lot

7883 Jackson Road, Ann Arbor, MI 48103, USA

Tel: 734-424-9327, Fax: 734-424-9328

Email: sales@bestungcarbideinc.com